RESEARCH ARTICLE

Open Access

Analysis of pigments and damages for the 19th century White-robed Water-moon Avalokitesvara Painting in Gongju Magoksa Temple, Republic of Korea

Hye Ri Yang, Chan Hee Lee* and Jeongeun Yi

Abstract

The *White-Robed Water-Moon Avalokiteshvara* painting displayed on the rear wall of Daegwangbojeon (main hall) in Magoksa temple, is one of the representative Buddhist paintings in the late nineteenth century of Korea, and a valuable resource for understanding the coloring techniques and characteristics of Buddhist paintings in terms of expression and description in landscape painting. In this painting, the contours and colored surface remain undamaged, but blistering and exfoliation appear on some pigment layers. Furthermore, the partial decomposition of wooden materials due to wood-decay fungi and insect damage were found on the rear wall requiring proper treatment for long-term conservation. As the results of chromaticity and P-XRF analysis regarding the color pigment layer of the painting, the pigments were classified into ten types. The results suggest that the colors other than blue, green, yellow, red, black, and white were prepared by mixing two or more pigments. The types of pigments according to colors, were determined as traditional pigments with azurite; emerald green or clinoatacamite; 0 massicot; minium or hematite; Chinese ink; and kaolin, white lead, and gypsum, respectively. Violet and pink colors were assumed to have been prepared by mixing white with blue and red. In most of these pigments, small amounts of synthetic compositions from the modern era were detected at many points.

Keywords: Magoksa temple, White-Robed Water-moon Avalokitesvara Painting, Coloring technique, Traditional pigment, Synthetic composition

Introduction

The major subjects of research related to the pigment analysis, reproduction, and restoration of colored cultural properties reported in South Korea over the past 30 years are pigments mixed in murals, Buddhist paintings, portraits, decorative paintings, documentary paintings, dancheong, and lacquerware. Analytical research on the pigments of temple murals makes up most of these studies, particularly focusing on artworks from

the seventeenth to nineteenth centuries during the late Joseon Dynasty (1392 to 1910) in Korea [1].

The paintings are found not only on the walls, ceilings, and pillars of the buildings, but there are also called of Taenghwa, Gyunghwa, and folding screen paintings. Despite the different time periods, research on Buddhist paintings has also been conducted; for instance, research on pigments [2], manufacturing techniques [3], pigment discoloration characteristics based on the environment [4, 5], and reproduction and restoration of traditional natural pigments [6].

Among these studies, identification of pigments for the Buddhist paintings are of fundamental importance for studying their manufacturing technology and residential

*Correspondence: chanlee@kongju.ac.kr

Department of Cultural Heritage Conservation Sciences, College of Natural Sciences, Kongju National University, Gongju 32588, Republic of Korea

environments, as well as for their conservation and restoration. Large scale banner paintings (Taenghwa) became popular in Korea during the seventeenth and eighteen centuries. The size and iconography of this type of painting suggest that they were originally important installations in monasteries. These paintings most likely hung behind a statue of Buddha Shakyamuni and would have been displayed in a hall dedicated to the Lotus Sutra or in some other major building within a temple complex [7, 8].

The *White-Robed Water-Moon Avalokiteshvara* is an artwork that represents the Buddhist paintings of Magoksa temple located on the rear wall on the west side of Daegwangbojeon (main hall), which is the dharma hall of Magoksa temple. A frame is made up of wood structures between high pillars, and several layers of mulberry fibers are applied to create a rear wall, which appears as if it were painted on a typical canvas. However, it is difficult to discover the exact date of creation because there is no manufacture date. In Magoksa temple, although this painting has been said to be painted by the Buddhist monk *māyā* Yakhyo (1846 to 1928), this claim is questionable because the expressions and descriptions of Amitabha about the crown of the white-robed *Gwaneum Bosal* (Buddhist Goddess of Mercy) are slightly different.

The lines are overall smooth, and the techniques of landscape paintings in the late Joseon Dynasty (seventeenth to nineteenth century) of Korea can be seen in the expression of the rocks. Nevertheless, considering the formal description technique observed in the face of Buddha and the use of dark red, the creation period is estimated to be in the late nineteenth century. Although the contours and colored surface of this *White-Robed Water-Moon Avalokiteshvara* remain undamaged, there is blistering, exfoliation, and discoloration of some pigment layers; contamination and stains; cracks and separations of the pigment layers; and cracks and separations of the wall. Thus, the painting urgently requires stable conservation treatment.

This painting was safely dismantled after performing a basic investigation and emergency treatment at the site. It was then transferred in a vibration-free vehicle for precise conservation treatment, and it has recently been placed at its original location. Prior to the conservation treatment of the painting, this study recorded the degree and condition of the overall damage in detail and conducted a scientific investigation on the colored layer to analyze the components and characteristics of the pigments used for coloring. Through such research, we have studied the characteristics by analyzing colored pigments used in ancient Korean art works [9, 10]. These results are important data that can reveal the pigments and coloring techniques used in Buddhist paintings at that time,

which also can be used for research on long-term preservation and repair.

Object and method

Object

Magoksa Temple was founded in 643 by the ancient Korean monk Jajang (590 to 658) with the support of Queen Seondeok during the Joseon Dynasty (fourteenth to nineteenth centuries). This temple gained widespread fame as one of the leading temples in the country under support from the royal family and the Provincial Office of Chungcheong Province. Moreover, Magoksa Temple was listed as a UNESCO World Heritage site in 2018 under the category of “Sansa, Buddhist Mountain Monasteries in Korea” in recognition of its historical and cultural value as a temple that has sustained the tradition and culture of the Buddhist community.

Magoksa Temple, surrounded by Mount Taehwa as a folding screen, is a space where monks’ and believers’ practices, beliefs, and lives blend together. It has served as a driving force for social integration and the preservation of traditions throughout Korean history. Daegwangbojeon Hall is Magoksa Temple’s dharma hall, rebuilt in 1788 and designated as Treasure No. 802. Inside Daegwangbojeon Hall, *Vairocana* Buddha is uniquely enshrined, facing towards the east from the building’s west wall. On the back wall of *Vairocana* Buddha, *White-Robed Water-Moon Avalokiteshvara* is also enshrined (Fig. 1).

This study was conducted prior to the conservation treatment of the *White-Robed Water-Moon Avalokiteshvara*, a Buddhist painting on the rear wall of main hall in Magoksa temple. It aimed to secure basic data can be used for conservation treatment through the precise analysis of coloring pigments by each color. Thus the surface of the painting as well as the integrity and damage status of the pigment layer were reflected in a drawing, which was intended to be preserved as a record of the repair and treatment areas of the colored layer.

This *White-Robed Water-Moon Avalokiteshvara* painting is a colossal mural measuring 515 cm in length and 296 cm in width, with *Gwaneum Bosal* (Avalokiteshvara) in a white robe sitting on a lotus pedestal above a rippling wave and a strange rocky stone, with her left leg hanging down. She is at the center of the painting surface and facing the front in a half-lotus position, her right leg placed on her left (Fig. 1a). *Gwaneum Bosal* wears a white robe from her head to below knees and red bottoms having a green bottom with red hem and tied with a pink belt inside the white robe (Fig. 2a).

In addition, *Gwaneum Bosal* wears a crown on her head with a standing Amitabha statue in the middle to indicate identity as *Avalokiteshvara* (Fig. 2b and c). Her right

Fig. 1 Location map and status showing the temple in Republic of Korea. **A, B** Map showing the location of research area. **C** Aerial photograph of Magoksa temple. **D, E** Frontal view and Cross-sectional diagram of Daegwangbojeon (main hall) in Magoksa temple

hand rests comfortably on right leg, and her right ankle is held with left hand. Her hands and feet are large and realistically depicted (Fig. 2d). Behind *Gwaneum Bosal*, four bamboo trees are rising from the rough rocks on the left side (Fig. 2e); *Seonjae Dongja* (priestling) stands thereunder, leaning toward *Gwaneum Bosal* (Fig. 2f); and a *kundika*, in which a willow branch is arranged, is placed on the opposite rocks (Fig. 2g).

Method

In the preservation status investigations, the damage types of the colored layer were subdivided to create a map, and empirical data were presented to increase the reliability. This study applied a method with recently proven reliability in the damage assessment in the field of cultural heritage conservation science, including stone artifacts [11, 12].

Damage map creation and non-destructive investigation for the painting as a research object were conducted with special care to prevent any impact on the painting by using an installed scaffold. First, the preservation status was precisely recorded by checking the damage status at the site, and the analysis target was further selected after selecting the colors, such as blue, green, yellow, red, black, and white, by visual observation to confirm the color status.

As the analysis point for each color, a site was selected, whose measurement area of approximately 5 mm in diameter was sufficient among the colors in which the difference in color was distinguished by visual observation, and where the pigment in the base layer with the target color was not disturbed (Fig. 3). Non-destructive chromaticity and composition measurements were performed for the selected analysis points, and a trace

Fig. 2 The present status of the *White-Robed Water-Moon Avalokiteshvara* painting in this study. **A** Foreground of the painting. **B** Face part of the painting. **C** Nirmāna-Buddha on crown. **D** Left hand of the painting. **E** Bamboo in the upper right corner. **F** *Seonjae Dongja* (priestling) in the center right. **G** *Kundika* and willow branches in the middle left

amount of pigment that had flaked off was collected by using a sample for precision analysis. The names of the analysis points are indicated in Table 1.

In the detail investigation, chromaticity measurement, observation through a portable stereoscopic microscope, and elemental analysis through a portable X-ray

fluorescence analyzer were performed. All were conducted through non-destructive analysis, and the same area was analyzed for each measurement item. Furthermore, the field analysis was carefully conducted by minimizing the applied pressure by selecting only the part of the color pigment that was most closely adhered onto the

Fig. 3 Photograph showing the detailed measurement points of P-XRF and chromaticity analysis in this study

base layer to avoid any loss from the split colored layer due to the contact-based analysis.

A total of 55 analysis points were used to identify the components of the color pigments in this painting for measurement under classification into blue, green, yellow, red, black, and white series. This study secured quantitative data based on the results of a color component analysis that had already been reported for this study, and the types of pigments used in this painting were identified in comparison to the data on previously studied traditional pigments [13–20].

A CM-2500d spectrophotometer (KONICA MINOLTA) was used to measure the chromaticity of the pigments, and three measurements were obtained at the same point with

a measurement area of 3 mm through the light source D65. The chromaticity values of the analyzed pigments were expressed by the CIELab system defined by the International Commission on Illumination (CIE), and the color coordinates were represented by luminosity (L^*), red to green value (a^*), and blue to yellow value (b^*). In addition, the color components can be more intuitively understood by indicating chromaticity (C^*_{ab}) and hue (h_{ab}) values on the polar coordinates. Chromaticity (Eq. 1) is expressed as a position between the center of the sphere (black) and the outer surface (white). Hue (Eq. 2) is expressed in angle, with red = 0°, yellow = 90°, green = 180°, and blue = 270° [21, 22].

$$C^*_{ab} = (a^{*2} + b^{*2})^{1/2} \quad (1)$$

$$h_{ab} = \arctan(b^*/a^*) \quad (2)$$

The measurement range of L^* is from 0 to 100, and 100 refers to nearly white, which is close to white light, and 0 refers to black. The measurement range of a^* and b^* for the colorimeter used in this study is −100 to +100. The a^* indicates a redder color in a positive direction and a greener color in a negative direction; b^* indicates a yellower color in a positive direction and a bluer color in a negative direction.

Meanwhile, molecular spectroscopic techniques are frequently applied in cultural heritage research. In particular, X-ray fluorescence (XRF) spectroscopy is extensively and successfully used for investigating objects of historical and cultural value, since it is non-destructive and, if necessary, measurements can be performed in situ, using portable equipment. The XRF provide valuable information regarding the material composition of artworks, contributing with substantial information about the time and geographical origin of an artifact or about production technologies [23].

Although XRF is an excellent technique for painting analysis, and it is widely used in literature, it does have some limitations. For example, because it is an elementary technique, pigments must to be identified indirectly by means of key elements associated with the colors observed in the painting. In this context, techniques that allow molecular analyses can bring information in order to complement the data obtained by XRF. In order to overcome these limitations of non-destructive analysis, a

Table 1 Summary on colors and designations for analysis points in this study

Color	Blue		Green	Yellow		Red	Black	White	Violet	Pink
	Blue-1	Blue-2		Yellow-1	Yellow-2					
Mark	LBG	SB	BG	OY	Y	R	BL	W	V	P

number of studies have been conducted to supplement it with analysis equipments [24–29]. However, all analysis results have their advantages and disadvantages, revealing some of the limited applications in this study where only non-destructive analysis was permitted without obtaining samples.

In this study, the component analysis for the color pigment at the site, an X-ray fluorescence spectrometer (P-XRF; Oxford Instruments, X-MET7500) was used for the part selected as the analysis location. The operating conditions of this spectrometer were an X-ray tube voltage of 15 to 40 kV (40 kV for heavy elements and 15 kV for light elements) and a current of 10 to 50 μ A. Measurement was performed in the ore mineral mode, the analysis area was approximately 5 mm in diameter, and the measurement time was 20 s each in conducting the elemental analysis on an atomic number of 15 or higher.

The pigments were identified based on the color associated with the presence of key-elements in the XRF spectra. In addition, the name of each pigment, even with the same components, may vary depending on the period, region, material, supply route, particle size, and areas of use. This study mainly recorded the names used based on previous studies regarding the color pigments of paintings. Furthermore, the estimation of black pigments and raw materials was performed through a comprehensive review of the results of scanning electron microscope-energy dispersive spectroscopy (SEM-EDS) analysis and X-ray fluorescence analysis performed in the field investigation by collecting a trace amount of color pigment samples that had flaked off during the stripping process.

Results and interpretation

Preservation status

The types of damage observed on the painting surface of *White-Robed Water-Moon Avalokiteshvara* are typically divided into microcracks (Fig. 4a), separation (Fig. 4b), fragmentation (Fig. 4c), contamination (Fig. 4d), and blistering and exfoliation of the pigment layer (Fig. 4e and f). Overall, although the contour lines and colored surfaces of this painting remain undamaged, damage appears on the painting surface along with blistering and exfoliation of some pigment layers, cracks and separation of the pigment layer, and cracks and separation of the wall (Fig. 4).

The blistering and exfoliation of the pigment layer are mainly observed around the face and on the red bottoms of the *Gwaneum Bosal*, which is believed to be accompanied by contraction, expansion, and cracking due to moisture. Moreover, after completely stripping the painting, the preservation condition of the wood materials on the rear wall were checked. As a result, it was found that the deterioration of the front lining paper and the wooden frame had severely progressed due to

decomposition by wood-decay fungi and insect damage (Fig. 4g and h).

The structural condition of the wooden frame constituting the painting wall was found to be relatively stable, and while there were cracks and separation along the edge of the wall, the preservation condition of the mural painting as a whole was fair. In addition, because the blistering, exfoliation of the colored layer, contamination, and fragmentation were found to be scattered throughout the painting surface, it was recommended that appropriate measures for long-term preservation be taken.

Chromaticity measurements

The pigments used to color this painting mainly include blue, green, yellow, red, black, and white, and violet and pink appear in smaller amounts (Fig. 5). This study measured the chromaticity of a total of 55 points for representative color pigments: six points for blue, eleven points for green, seven points for yellow, eight points for red, six points for black, eleven points for white, and ten points for other colors (Fig. 6 and Table 2).

The chromaticity values for all measurement points represent various luminosity values, which are distributed between red to yellow (h_{ab} : 0 to 90°) and yellow to green (h_{ab} : −90 to 0°) as a result of projection on the CIE Lab quadrant. Among the values, yellow and red pigments have relatively higher chromaticity and hue variability than blue and green pigments (Table 2, Fig. 6).

Regarding the chromaticity range of the blue-1 pigment, L^* , a^* , and b^* range from 65.5 to 65.62 (mean 65.56), −1.77 to −0.8 (mean −1.285), and 10.25 to 12.87 (mean 11.56), respectively. Regarding the chromaticity of the blue-2 pigment, L^* on means is 70.71, a^* is −5.07, and b^* is 10.52, respectively. Blueness increases as b^* increases in the negative direction, while the measured blue-2 pigments all have positive b^* values, showing that the blueness of the blue-2 pigments is lower than that of the blue-1 pigments (Table 2 and Fig. 6).

According to the result of measuring the chromaticity for the green pigments, L^* , a^* , and b^* range from 42.18 to 54.82 (mean 48.00), −15.7 to −3.87 (mean −10.16), and 3.75 to 6.57 (mean 2.71), respectively. As a^* increases in the negative direction, greenness increases, and the a^* values of all analysis points are negative. BG-7 shows the highest green level with a L^* of 53.88, a^* of −15.7, and b^* of 11.75, and BG-10 shows the lowest green level with a L^* of 44.14, a^* of −3.87, and b^* of 4.81 (Table 2 and Fig. 6).

Regarding the chromaticity of the yellow-1 pigments, L^* , a^* , and b^* range from 54.53 to 60.56 (mean 57.41), 9.36 to 11.75 (mean 10.67), and 22.62 to 28.75 (mean 26.39), respectively. In the case of the yellow-2 pigments, L^* , a^* , and b^* range from 56.64 to 61.02 (mean 57.41),

Fig. 4 Photographs showing the representative damages of the studied painting. **A** Microcracks. **B** Separation. **C** Fragmentation. **D** Black contamination. **E** Blistering and exfoliation of the pigment layer. **F** Stereoscopic photographs of the exfoliation part on the pigment layers. **G** Deterioration of wooden frame after stripping the painting. **H** Residual pigments and cracks in the wooden frame

0.52 to 5.75 (mean 3.38), and 26.61 to 37.08 (mean 30.54), respectively. Yellowness increases as b^* increases in the positive direction. Y-3 shows the highest yellowness, and OY-3 shows the lowest yellowness (Table 2 and Fig. 6).

The chromaticity of red pigments is widely distributed in the $+a^*$ and $+b^*$ coordinate planes. L^* , a^* , and b^* range from 32.96 to 6.22 (mean 39.92), 12.71 to 30.39 (mean 20.67), and 14.45 to 19.68 (mean 17.28), respectively.

Redness increases as a^* increases in the positive direction. R-2 shows the highest redness with a L^* of 38.38, a^* of 30.39, and b^* of 17.43, and R-8 shows the lowest redness with a L^* of 46.22, a^* of 12.71, and b^* of 16.47 (Table 2 and Fig. 6).

The chromaticity range of black pigments is concentrated near the origin. L^* , a^* , and b^* range from 25.42 to 58.65 (mean 34.51), 0.25 to 8.95 (mean 1.80), and 1.27 to 25.9 (mean 6.59), respectively. The analysis

point closest to the origin is BL-1, where L^* is 25.43, a^* is 0.25, and b^* is 1.27. The chromaticity range of white pigments is distributed vertically along the $+b^*$ axis. L^* , a^* , and b^* range from 53.87 to 80.72 (mean 73.99), -2.55 to 2.89 (mean 1.02), and 8.36 to 21.78 (mean 16.09), respectively. The analysis point with the lightest color corresponds to W-8, and the analysis point with the darkest color corresponds to W-9 (Table 2 and Fig. 6).

Fig. 6 Diagrams showing the chromaticity analysis for coloring pigments in this study. **A** Luminosity. **B** Position of the analysis points projected in the a^*b^* plane. The abbreviations are shown in Table 1 and the symbols are shown in Fig. 6

Table 2 Descriptive values statistics (mean, standard deviation, maximum and minimum) for the CIELab colour parameters of the painting in this study

			L*	a*	b*	C* _{ab}	h _{ab}				L*	a*	b*	C* _{ab}	h _{ab}
Blue	1	Mean	65.56	− 1.29	11.56	65.56	96.15	Red	Mean	39.92	20.72	17.04	39.92	40.10	
		SD	0.08	0.69	1.85	0.69	2.38		SD	3.80	5.02	2.37	5.02	8.17	
		Max.	65.62	− 0.80	12.87	12.87	97.83		Max.	46.22	30.39	19.68	19.68	52.34	
		Min.	65.50	− 1.77	10.25	10.28	94.46		Min.	32.96	12.71	12.45	20.80	29.07	
	2	Mean	70.71	− 5.08	10.52	70.71	116.09	Black	Mean	34.52	1.81	6.59	34.52	79.22	
		SD	2.39	0.97	1.49	0.97	6.68		SD	12.92	3.50	9.54	3.50	4.84	
		Max.	72.89	− 3.73	12.17	12.17	122.15		Max.	58.65	8.95	25.86	25.86	85.80	
		Min.	68.06	− 6.04	8.96	10.46	108.21		Min.	25.42	0.25	1.27	1.29	70.91	
Green	Mean	48.01	− 10.17	4.12	48.01	156.76	White	Mean	73.35	0.84	15.78	73.35	87.85		
	SD	5.08	3.88	3.36	3.88	15.76		SD	8.48	1.64	4.43	1.64	6.21		
	Max.	56.50	− 3.87	11.75	11.75	184.27		Max.	80.72	2.66	21.78	21.78	101.85		
	Min.	42.18	− 15.70	− 1.10	5.80	128.82		Min.	53.87	− 2.55	8.36	8.36	82.34		
Yellow	1	Mean	57.41	10.68	26.40	57.41	67.90	Violet	Mean	52.35	− 0.57	− 1.24	52.35	61.20	
		SD	3.19	0.99	2.93	0.99	1.95		SD	1.32	0.18	0.71	0.18	20.66	
		Max.	60.56	11.75	28.75	28.75	69.50		Max.	53.28	− 0.44	− 0.74	− 0.74	75.81	
		Min.	54.53	9.36	22.62	24.48	65.30		Min.	51.42	− 0.70	− 1.74	1.02	46.59	
	2	Mean	59.41	3.38	30.54	59.41	83.94	PINK	Mean	64.87	9.26	13.80	64.87	53.42	
		SD	2.41	2.65	5.70	2.65	4.33		SD	2.43	5.67	3.33	5.67	9.14	
		Max.	61.02	5.75	37.08	37.08	88.93		Max.	68.42	17.21	18.43	18.43	59.88	
		Min.	56.64	0.52	26.61	26.89	81.19		Min.	62.92	3.91	10.65	13.76	46.96	

SD standard deviation

Meanwhile, regarding the chromaticity range of violet pigments, L^* , a^* , and b^* range from 51.42 to 53.28 (mean 52.35), -0.74 to -0.44 (mean -0.57), and -1.74 to 0.74 (mean -1.24), respectively. Because a^* and b^* show negative values at both measurement points, the redness and yellowness are not high, which does not deviate significantly from the negative direction. Furthermore, regarding the chromaticity range of pink pigments, P-1 shows higher redness and yellowness than P-4 (Table 2 and Fig. 6).

Chemical compositions by P-XRF

P-XRF was utilized to analyze the chemical composition of pigments in *White-Robed Water-Moon Avalokiteshvara* painting. The analysis locations were the same as the points for the chromaticity measurement and observation using the stereoscopic microscope. The analysis location for each colored pigment is shown in Fig. 6.

In analyzing a pigment layer through P-XRF, it is difficult to accurately measure only the pigment compositions because X-rays penetrate through the thin pigment layer and further analyze the underlying background. To overcome these shortcomings, studies have aimed to unravel only the components of the pigment from which the background component was removed. This study also detected the compositions of the pigment layer according to the method provided by Lee et al. [2] and Kim and Lee [10].

Two types of blue pigments were used for the basic coloring of this painting. According to the results of chromaticity measurement and observation using the stereoscopic microscope, an analysis was conducted by classifying the results into Blue-1 and Blue-2. If grayish blue ($(\text{Co}, \text{Ni})\text{As}_3$) is used as a blue pigment, cobalt and nickel compositions are detected. However, these were not detected in this painting. On average, 9037 ppm (6363 to 11,710 ppm) and 33,763 ppm (12,844 to 59,991 ppm) of Cu were detected in Blue-1 and Blue-2 analysis points, respectively.

Thus, the results suggest that the color depth was raised by mixing a white pigment with azurite ($\text{Cu}_3(\text{CO}_3)_2(\text{OH})_2$), which is one of the traditional blue pigments. The detection of the high concentration of Ca, Pb, and S compositions at all analysis points further suggests that the color shade could have been adjusted by oyster shell white (CaCO_3) or white lead ($2\text{PbCO}_3 \cdot \text{Pb}(\text{OH})_2$) (Table 3 and Fig. 7).

According to the results of the P-XRF analysis regarding the green pigment layer measured at a total of 11 points, the major compositions detected were elements such as S, Ca, Ti, Fe, Cu, As, and Pb. However, the average content of Cu and As showed a significant difference: 149,915 ppm (13,321 to 311,848 ppm) and

110,568 ppm (13,716 to 296,732 ppm). Typically, when Cu and As are simultaneously detected in the composition of a green pigment, it is considered emerald green ($\text{Cu}(\text{C}_2\text{H}_3\text{O}_2)_2 \cdot 3\text{Cu}(\text{AsO}_2)_2$). However, in the relative content ratios of emerald green, the content of As is much higher than that of Cu. Although a high As content was detected in the green pigment used in this painting, it was difficult to determine it as emerald green because the ratio of As was mostly lower than that of Cu (Table 3 and Fig. 7).

The difference in the Cu and As content at each analysis point may have been affected by the thickness of the overlapped color. Furthermore, the pigments used for the face of Buddha and *Keyura* accessories remained relatively undamaged, whereas those used on the feet and the lower parts fell off, resulting in a relatively small amount. Thus, these results suggest that clinoatacamite ($\text{Cu}_2(\text{OH})_3\text{Cl}$) made up of copper-based raw materials was mainly used for the green pigment layer, and it was likely painted over by modern pigments given the result that the Ca and Cl content is relatively high at some points (Table 3 and Fig. 7).

The points classified as yellow were analyzed by dividing them into Yellow-1 and Yellow-2 according to the results of chromaticity measurement and observation using the stereoscopic microscope. Among the main constituent elements detected, Al and Si appear to have been simultaneously detected as a dead color paint component using a white pigment, such as *urnā* (Table 3). The content of Pb was the highest at all points with an average of 288,094 ppm (246,801 to 323,689 ppm) and 252,850 ppm (187,988 to 289,484 ppm), in Yellow-1 and Yellow-2, respectively, followed by S with an average of 90,707 ppm (59,470 to 132,885 ppm) and 140,291 ppm (133,392 to 151,7544) (Table 3 and Fig. 7). Thus, the color yellow can be assumed to lower the chromaticity by mixing white pigments with massicot.

However, the detection of As (6014 ppm) only in Y-1 suggests that orpiment (As_2S_3) and massicot (PbO) were mixed with a white pigment for coloring. Regarding the white pigment used in the color combination, the Ti content was relatively high at 72,827 ppm (58,638 to 81,718 ppm) and 72,400 ppm (51,038 to 83,346 ppm) in Yellow-1 and Yellow-2, respectively, which can be assumed to be titanium dioxide (TiO_2). In addition, compared to other color pigments, Ba is highly likely to be a modern pigment due to the detection of high levels of Ba with an average of 55,919 ppm (46,032 to 74,7499 ppm) and 67,742 ppm (56,966 to 82,836 ppm) in Yellow-1 and Yellow-2, respectively (Table 3 and Fig. 7).

According to the results of the component analysis on red pigments, the main composition were Pb, S,

Table 3 Representative concentratios (ppm) by P-XRF of pigments on the studied painting

No		Si	Al	Fe	Ti	Ca	Mg	K	S	Cl	As	Ba	Cu	Hg	Pb
Blue-1	Mean	188,019	69,928	18,726	1,134	214,938	ND	8,426	55,078	ND	4,285	ND	9,037	ND	5,707
	SD	39,246	23,248	18,419	158	98,813	ND	11,915	17,751	ND	2,270	ND	3,781	ND	ND
	Max.	215,770	86,366	31,750	1,246	284,809	ND	16,851	67,630	ND	5,890	ND	11,710	ND	7,713
	Min.	160,268	53,489	5,702	1,022	145,067	ND	ND	42,526	ND	2,680	ND	6,363	ND	3,701
Blue-2	Mean	119,355	50,436	9,147	1,121	341,514	ND	1,359	57,663	ND	4,228	ND	33,763	ND	9,470
	SD	2,029	4,718	4,888	149	30,790	ND	2,717	14,518	ND	309	ND	24,317	ND	8,068
	Max.	121,166	56,648	14,074	1,265	368,397	ND	5,434	78,262	ND	4,616	ND	59,991	ND	17,536
	Min.	117,417	45,759	4,783	930	307,801	ND	ND	45,364	ND	3,880	ND	12,844	ND	2,515
Green	Mean	115,166	42,613	25,780	766	35,175	30,524	23,684	28,938	24,820	110,568	ND	149,915	46	18,180
	SD	73,632	21,629	23,358	623	50,422	32,902	20,590	12,510	14,286	76,859	ND	94,787	153	23,602
	Max.	261,796	72,956	80,064	1,947	148,206	80,061	67,626	49,617	47,419	296,732	ND	311,848	507	74,405
	Min.	54,172	ND	7,202	ND	3,609	ND	6,208	11,315	ND	13,716	ND	13,321	ND	ND
Yellow-1	Mean	66,816	ND	7,555	ND	11,017	ND	1,782	90,707	ND	ND	55,919	8,756	548	288,094
	SD	8,041	2,975	1,902	11,116	7,225	ND	3,564	34,826	4,720	ND	12,828	5,766	866	31,603
	Max.	77,951	19,286	9,885	81,718	17,343	ND	7,128	132,885	30,303	ND	74,749	14,337	1,820	323,689
	Min.	58,842	12,453	5,526	58,638	4,424	ND	ND	59,470	19,529	ND	46,032	3,510	ND	246,801
Yellow-2	Mean	60,278	14,611	12,199	72,400	3,727	ND	5,764	140,291	29,398	2,005	67,742	6,389	ND	252,850
	SD	7,837	3,079	4,394	18,502	1,900	ND	4,992	9,996	6,403	3,472	13,465	398	ND	56,329
	Max.	68,560	17,255	15,254	83,346	5,877	ND	8,684	151,754	36,457	6,014	82,836	6,707	ND	289,484
	Min.	52,979	11,230	7,164	51,038	2,277	ND	ND	133,392	23,966	ND	56,966	5,943	ND	187,988
Red	Mean	109,215	51,483	56,471	17,933	30,023	ND	11,647	126,608	27,071	241	20,687	4,008	5,520	187,009
	SD	67,900	51,070	47,584	20,026	28,673	ND	3,936	47,290	25,416	462	24,411	2,008	7,667	191,981
	Max.	208,888	141,941	144,556	56,922	65,373	ND	16,945	176,624	59,990	1,184	66,173	7,032	16,299	373,432
	Min.	30,988	8,371	13,311	943	2,229	ND	6,850	42,744	ND	ND	ND	1,765	ND	ND
Black	Mean	196,408	81,706	28,058	1,976	85,953	ND	33,818	71,263	19,528	1,054	ND	3,348	ND	59,164
	SD	76,697	39,621	14,544	507	75,135	ND	17,405	41,787	30,856	1,342	ND	2,565	ND	133,429
	Max.	252,724	122,297	46,489	2,514	194,497	ND	55,483	125,777	68,180	3,000	ND	7,576	ND	331,475
	Min.	63,842	16,992	11,076	1,098	16,859	ND	12,746	35,642	ND	ND	ND	678	ND	ND
White	Mean	151,220	42,596	13,109	4,440	225,922	39,842	7,623	47,701	3,594	803	7,159	2,140	ND	48,402
	SD	69,768	29,725	8,795	3,905	70,754	69,479	8,007	23,056	11,918	1,003	12,349	2,351	ND	96,896
	Max.	244,566	89,153	27,255	11,088	341,179	175,919	24,628	98,436	39,529	2,952	28,798	7,406	ND	316,554
	Min.	58,740	ND	4,361	1,039	95,963	ND	ND	ND	ND	ND	ND	559	ND	571
Violet	Mean	234,391	51,155	26,454	917	34,920	73,223	21,793	72,511	ND	442	ND	27,799	ND	7,934
	SD	13,900	3374	4,524	130	3,895	2,331	3,268	8,832	ND	624	ND	7,828	ND	277
	Max.	244,220	53,541	29,653	1,009	37,674	74,871	24,104	78,756	ND	883	ND	33,334	ND	8,130
	Min.	224,562	48,769	23,255	825	32,165	71,575	19,482	66,265	ND	ND	ND	22,263	ND	7,738
Pink	Mean	177,186	20,127	11,374	8,137	109,155	96,045	8,041	33,532	4,188	150	10,220	5,786	ND	99,309
	SD	89,135	13,519	4,724	4,925	130,723	67,834	5,850	29,904	8,377	300	8,607	6,068	ND	123,079
	Max.	230,166	28,167	16,438	13,734	304,902	158,080	13,997	71,002	16,753	599	20,948	13,953	ND	277,324
	Min.	43,800	ND	7,037	1,758	34,669	ND	ND	ND	ND	ND	ND	1,115	ND	2,228

ND not detected

Numbers are the same as those of Fig. 2

Abbreviations as in Table 1

and Hg, and Si and Al were detected at all measured points. It can be assumed that the colored white clay under the red layer was detected together with the pigments. According to the results of the P-XRF analysis

regarding a total of eight points, the patterns of constituent elements were classified into two, depending on the presence and content of Fe, Pb, and Hg.

Points R-1 to R-4 show a high Pb content with an average of 366,476 ppm (360,982 to 373,432 ppm). Points R-5

Fig. 7 Diagrams showing the measurement results (ppm) of coloring pigments by P-XRF in this study. Numbers are the same as those of Fig. 2

to R-8 show a relatively high content of Fe, with an average of 94,592 ppm (63,070 to 144,556 ppm). Thus, the red colors appear to be a mixture of minium (Pb_3O_4) or minium and hematite (Fe_2O_3), and it can be assumed that

cinnabar (HgS) was used in smaller amounts together with these (Table 3 and Fig. 7).

According to the analysis results regarding the black layer, elements such as P, Fe, K, S, Ca, Ti, Cl, and Cu were detected. Most of these elements are not components of

black pigments, which suggests the effect of dead color paints. However, no element indicating black color was detected (Table 3 and Fig. 7). The traditional black pigment is an Chinese ink, which is a carbon compound. Because Chinese ink is composed of light elements, it is difficult to detect with P-XRF. Thus, because only the same components as the white pigment used in the base layer were mainly detected at the measurement point of the black pigment, Chinese ink was likely used for black color development, requiring additional review.

In this black layer, the detection of slightly high levels of Pb and Ca, with an average of 59,164 ppm (0 to 331,475 ppm) and 85,953 ppm (from 16,859 to 194,497 ppm) through P-XRF, suggests that white lead and oyster shell white were mixed to lower the concentration of black pigment. Among the analysis points, the highest detection of Pb at 331,475 ppm in the right pupil of the *Gwaneum Bosal* statue suggests that the pigment was reapplied several times (Table 3 and Fig. 7).

The white color is mainly used on the *Gwaneum Bosal* statue and cloth, in which elements such as Si, K, and Al were detected through the P-XRF analysis. Among these elements, the average contents of Si, K, and Al were 151,220 ppm (58,740 to 244,566 ppm), 11,979 ppm (5,722 to 24,628 ppm), and 46,856 ppm (7,846 to 89,153 ppm), respectively, and these high levels suggest the high likelihood of the use of kaolin ($\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4$). The detection of Ca and S with an average of 225,922 ppm (95,963 to 341,179 ppm) and 52,471 ppm (36,456 to 98,436 ppm) suggests that gypsum was likely mixed with feldspathic kaolin (Table 3 and Fig. 7).

The color violet was mainly used for coloring the *daeui* part of *Gwaneum Bosal*. According to the result of the P-XRF analysis, Cu and Fe were detected with an average of 27,799 ppm (22,263 to 33,334 ppm) and 26,454 ppm (23,255 to 29,653 ppm), respectively, as the main compositions. Because the composition is similar to that of the blue pigment, and high levels of Fe and Pb are detected, the mixture of azurite, hematite, and minium can be assumed (Table 3 and Fig. 7).

In addition, Ca, S, and Mg were detected here at 34,920 ppm (32,165 to 37,674 ppm), 72,511 ppm (66,265 to 78,756 ppm), and 72,223 ppm (71,575 to 74,871 ppm), respectively. This result suggests the addition of gypsum or talc ($\text{Mg}_3\text{Si}_4\text{O}_{10}(\text{OH})_2$), which is a white pigment, or the detection of constituent minerals in the base layer to lower the chromaticity (Table 3 and Fig. 7).

The color pink is painted on the chest top part of *Gwaneum Bosal* as well as the ears of Buddha. According to the results of the P-XRF analysis, Si, Mg, Ca, and S were detected with an average of 177,186 ppm (43,800 to 230,166), 128,059 ppm (104,302 to 158,080 ppm), 109,155 ppm (34,669 to 304,902 ppm), and 44,710 ppm

(23,002 to 71,002 ppm), respectively. This result becomes the basis for assuming the use of kaolin or talc as a white pigment in combination with pink. Moreover, the detection of high levels of Pb and Fe with an average of 99,309 ppm (2228 to 277,324 ppm) and 11,374 ppm (7,0378 to 16,438 ppm) suggests that the color depth was raised by mixing kaolin or talc with minium and hematite in terms of components (Table 3 and Fig. 7).

SEM-EDS analysis

Although the locations of the micro-fragments of the flaked-off pigments collected during the stripping process for the repair of the *Gwaneum Bosal* were not clearly identified on this painting, a pale blue pigment was found underneath the thin black layer. Based on this finding, the colored layer was closely observed on a SEM (TESCAN, MIRA3), and the constituent elements on the pigment layer were analyzed using an EDS (Bruker, Quantax 200) mounted onto the SEM (Fig. 8).

According to the observation at high magnification with the SEM, the microtextures of the pigment layer can be divided into two layers: a black layer and a cyan layer (Fig. 8c). The elemental mapping regarding the black pigment part confirmed that carbon was more distributed in the black part than in the light cyan part (Fig. 8e). An observation at 3000 magnification of this part showed that carbon particles with a diameter of 5 nm were relatively uniformly coated on the smooth surface (Fig. 8f).

According to the results of the EDS analysis regarding this matter, a significantly high carbon (C) content was detected with an average of 60.30 wt.% (Table 4). In particular, no compositions other than the base layer components underneath the black color were detected, suggesting that Chinese ink, which is composed mainly of carbon, was used for coloring (Fig. 8c to g, and Table 4). Furthermore, although the SEM analysis regarding the pigments attached to the background paper showed a large number of Blue-1 pigment particles that had exfoliated onto the tissue composed of mulberry fibers, no specific components were detected (Fig. 8b and h).

Discussions

This study secured basic data on the types, compositions, raw materials, and colors of the pigments used in this painting through a scientific investigation and precise analysis of *White-Robed Water-Moon Avalokiteshvara* of main hall in Magoksa temple and the pigments remaining on the wooden frame after its stripping. The Korean National Research Institute of Cultural Heritage has reported on traditional pigments and color-developing elements based on analysis of various periods and cultural heritages. Table 5 summarizes the pigments that are

Fig. 8 Microphotograph images using optical microscope, SEM and EDS analytical spots for exfoliated black and cyan pigment samples in this study. **A, B** Occurrences under stereoscopic microscope at the analysis point. **C** SEM secondary electron image in Fig. 3A. **D** SEM Back scattered electron image of Fig. 3A. **E** Elemental mapping image using EDS analysis on the black and cyan layer. **F** SEM secondary electronic images of carbon particles in Fig. 3A. **G** Enlarged particle image of Fig. 3F. **H** SEM secondary electron image in Fig. 3B

consistent with the manufacturing time and color of this study subject based on data from previous studies.

Based on this data, in reviewing the analysis results regarding the target of this study, small amounts

of modern synthetic pigments were identified at many points. Table 5 shows the results of the analysis using P-XRF and SEM-EDS, which are classified into the

Table 4 Results of SEM–EDS analysis (wt.%) on samples after exfoliation from the painting in this study

No.	Si	Al	Fe	Ca	Mg	Na	K	C	O
1	14.62	8.24	0.62	–	0.91	1.32	2.51	24.81	46.97
2	6.01	3.39	0.65	0.3	0.88	0.55	1.09	67.42	19.71
3	3.83	4.37	0.74	1.41	9.12	–	1.05	54.36	25.12
4	15.7	4.34	1.63	–	5.9	0.18	2.25	22.64	47.36
5	6.62	3.51	1.45	0.89	7.67	–	1.41	49.65	28.8
6	3.84	4.14	0.71	1.42	9.15	–	1.12	54.33	25.29
7	1.26	1.46	0.7	1.36	–	–	0.85	85.57	8.8
8	1.43	0.88	1.24	0.63	0.24	–	0.87	88.12	6.59

The measuring points are shown in Fig. 7

Table 5 A summary of representative main pigments used in Korean Buddhist paintings from the eighteenth to nineteenth centuries analyzed in previous studies on historical wall paintings

Color	Pigment	Formula	References
Blue	Azurite	$\text{Cu}_3(\text{CO}_3)_2(\text{OH})_2$	[5, 10]
	Smalt	$\text{SiO}_2 \cdot \text{K}_2\text{O} \cdot \text{CoO}(\text{Co,Ni})\text{As}_3$	
Green	Celadonite	$\text{K}(\text{Mg,Fe})(\text{Fe,Al})\text{Si}_4\text{O}_{10}(\text{OH})_2$	[24, 31]
	Emerald green	$\text{Cu}(\text{C}_2\text{H}_3\text{O}_2)\text{Cu}(\text{AsO}_2)_2$	
Yellow	Massicot	PbO	[10]
	Orpiment	As_2S_3	
Red	Cinnabar	HgS	[20, 26]
	Hematite	Fe_2O_3	
	Minimum	Pb_3O_4	
Black	Chinese ink	C	[9, 19]
	Black Oxide	unknown	
White	Kaolinite	$\text{Al}_2\text{SiO}_5(\text{OH})_4$	[30, 32]
	Oyster Shell white	CaCO_3	
	Lead White	$2\text{PbCO}_3 \cdot \text{Pb}(\text{SO}_4)_2$	

color series of pigments according to major color-developing elements.

Two types of blue pigments were assumed to be used for raising the color depth by mixing a white pigment with azurite ($\text{Cu}_3(\text{CO}_3)_2(\text{OH})_2$). Regarding the average chromaticity, L^* , a^* , and b^* are 11.6, 65.6, and -1.3 , respectively, for Blue-1 pigment and 70.7, -5.1 , and 10.5 for Blue-2. The higher L^* value for Blue-2 suggests that Blue-2 was mixed with a larger amount of white pigment to lower the chromaticity. The white pigment used in this case is assumed to be white lead, kaolin, or titanium dioxide (Table 6).

As pigments that are color development sources for green, copper chloride-based emerald green and clinoat-acamite were identified, and white pigments such as white lead and kaolin were used as auxiliary materials for color combination, depending on the coloring position. The average chromaticity of the green series was determined as a L^* of 48.0, a^* of -10.2 , and b^* of 4.1, and the chromaticity varied slightly depending on each analysis point.

Orpiment and massicot were identified as yellow pigments. These two types of yellow colors were mixed with white pigments to adjust their chromaticity for color

Table 6 Summary on detected elements and estimated pigments for the painting in this study

Color	Major elements	Minor elements	Interpreted pigments
Blue-1	Cu	Fe, Ti, Ca, Mg, Na, K, S, Cl, As, Pb, Zn	Azurite + Lead White or White Clay
Blue-2	Cu	Fe, Ti, Ca, Mg, K, S, Cl, As, Pb	
Green	Cu, Cl	Fe, Ti, Ca, Mg, K, S, As, Co, Pb	Emerald Green, Clinoatcamite
Yellow-1	Pb, S	Fe, Ti, Ca, Mg, K, Cl, As, Ba, Cu, Hg	Litharge on Lead White
Yellow-2	Pb, S	Fe, Ti, Ca, Mg, K, Cl, As, Ba, Cu	
Red	Fe, Pb, Hg, S	Ti, Ca, K, Cl, Ba, Cu	Hematite, Red Lead (or Cinnabar)
Black	C	Fe, Ti, Ca, Mg, K, S, Cl, As, Cu, Pb, Zn	Chinese Ink
White	Al, Si, Pb	Mg, P, S, Ca, Ti, Mn, Fe, Cu, Zn, As, Ba	Lead White and White Clay
Violet	Cu, Fe, Pb	Ti, Ca, Mg, Mn, K, S, As, Zn	Azurite + Hematite + Lead White
Pink	Ca, Pb	Fe, Ti, Mg, K, As, Cu	Red Lead and Oyster Shell W

combination. S and Pb were highly detected at most of the measurement points, suggesting that massicot (PbO) was likely used in combination with white lead or gypsum.

A trace amount of As was detected at the Yellow-2 point, which was difficult to determine as orpiment (As_2S_3) because the pigments colored on the background may have been analyzed together with it. The average chromaticity of Yellow-1 was determined as a L^* of 57.4, a^* of 10.7, and b^* of 26.4, and that of Yellow-2 was determined as a L^* of 59.4, a^* of 3.4, and b^* of 30.5. Thus, Yellow-1 was higher in luminosity, while Yellow-2 was higher in yellowness.

The compositions of Fe, Pb, S, and Hg were detected as color development sources for red pigments, which have compositions of hematite, cinnabar, and minium in common. This result suggests a mixture of hematite and minium as well as white pigments, such as lead and kaolin, for color combination. Mercury (Hg)-based cinnabar appears to have been used in trace amounts, or not used at all. According to the existing records, because cinnabar was highly expensive—with a value approximately three times that of Hg—*Seokganju* was used as a substitute it [30].

Among these analysis points, 56,922 ppm of Ti was detected in R-2, which suggests that titanium dioxide was likely used. The average chromaticity of red pigments including various color ranges was determined as a L^* of 39.9, a^* of 20.7, and b^* of 17.0, showing a tendency of low chromaticity and redness, and there was no significant difference in the average values of chromaticity for each measurement point.

The black pigments were all assumed to be amorphous Chinese ink. Chinese ink and *niram* were mainly used as black pigments in Buddhist paintings or *dancheong*, making it difficult to accurately identify via P-XRF analysis alone. To overcome the limitations of this non-destructive analysis, a UV-Vis analysis was additionally performed for *Gwaebultaeng* in Boeun Beopjusa Temple (Treasure No. 1259). The results indicated that the reference spectra of the artifact's black pigment was nearly identical to that of Chinese ink [10]. However, the application of this technique was not permitted in the present study.

The average chromaticity of the black series was determined as a L^* of 59.4, a^* of 3.4, and b^* of 30.5, showing no significant difference at most of the analysis points, whereas the black pigment used for coloring the bamboo in the top right corner of *Gwaneum Bosal* showed the highest values with a L^* of 49.92, a^* of -10.91 , and b^* of 1.75.

Kaolin and white lead were identified as pigments that become color development sources for the color white.

Kaolin is composed of various minerals, which are subdivided into kaolinite with feldspar, and mica. The results suggest that white pigments were used alone, mixed with pigments of other colors, or used as extenders. The average chromaticity of the white pigments was determined as a L^* of 74.0, a^* of 1.0, and b^* of 16.1.

Violet and pink were used as auxiliary colors for coloring this painting. The analysis results of pigments showed that their composition was similar to that of the blue pigments, and the detection of Fe and Pb indicated that white lead was mixed with azurite or hematite. The average chromaticity of the color violet was determined as a L^* of 52.4, a^* of -0.6 , and b^* of -1.2 , which has lower chromaticity and higher blueness than the blue pigments.

The pink pigments were estimated to be a mixture of minium and oyster shell white due to the detection of high levels of Ca and Pb at almost all measurement points. Furthermore, the results suggested that Mg, Al, and Fe were detected at the measurement points of P-2 to P-4 due to the influence of the base layer. The average chromaticity of the pink pigments was determined as a L^* of 63.7, a^* of 11.0, and b^* of 13.8, which shows high luminosity and slight reddishness.

Elements such as Ti, Ba, and Hg were identified in most points on this painting, and thus, it was impossible to rule out the possibility that industrial synthetic pigments were used in the repair process. Research results reveal that pigments were imported from China or the Western Regions, suggesting a high likelihood that *White-Robed Water-Moon Avalokiteshvara* was repaired using modern pigments even though South Korea started manufacturing modern pigments in 1940.

Further research is required, such as more accurate component analysis and identification for each color of the pigment, to confirm the traditional pigments that were used prior to modern synthetic pigments. Table 6 summarizes the analysis results and estimated pigments for the aforementioned ten types of pigments.

Meanwhile, Ca, Fe, As, and Cu components were concurrently detected through the pigments' analysis points. This finding could be attributed to dead coloring, which is one of the production techniques of traditional painting. Dead coloring is applied on the ground layer of paper, silk, or burlap used as materials in Buddhist paintings and folk tales. This technique impedes the absorptency of the ground layer, improves the coloring of the recoated pigments, and serves as a filler for pores or grain. Dead coloring was applied to nearly all ancient Korean paintings, and the same is true for modern Buddhist paintings and oil paintings [10].

There are some examples in which green pigment was used as a dead color paint in Buddhist paintings, and the ground layer of *Dancheong* was repainted using *noerok*.

Thus, there is a likelihood that green pigments were also used as a dead color paint for *White-Robed Water-Moon Avalokiteshvara*. Concurrent detection of certain components—such as Ca, Fe, As, and Cu—could be attributed to kaolin and massicot containing Ca and Fe, which were often used as fillers for the ground layer. Moreover, Cu and As will also be detected assuming that green pigments were used as a dead color paint. To prove this assumption, additional cross-sectional observations of the applied pigments and/or studies focusing on other Buddhist paintings are necessary.

Amorphous carbon was observed in the black pigment remaining on the wooden frame after this painting was stripped. Although P, S, and Pb were also detected, this was assumed to be due to interference from the contaminants and the surrounding pigments. In addition, green, white, grayish white, and red pigments appeared, and the element content ratio of each color pigment was highly similar to that of this painting. Thus, the pigments remaining on the wooden frame are assumed to have been influenced by the pigments used in this painting.

Conclusions

The *White-Robed Water-Moon Avalokiteshvara* painting displayed on the rear wall of main hall in Magoksa temple, is painting representative of Buddhist paintings in the late nineteenth century of Korea, and a valuable resource for understanding the coloring techniques and characteristics of Buddhist paintings in terms of expression and description methods in landscape painting. The present study has applied a non-destructive method to analyze the eighteenth-century South Korean *White-Robed Water-Moon Avalokiteshvara* to determine which pigments were used for coloring.

Table 5 summarizes the estimated pigments. In total, 45 different colors and compositions were analyzed under the same conditions, and the pigments used for each color were examined based on the components detected via qualitative analysis. As a result, the types of pigments according to color, blue, green, yellow, red, black, and white were determined as azurite; emerald green or clinoatacamite; massicot; minium or hematite; Chinese ink; and kaolin, white lead, and gypsum, respectively. Violet and pink colors were assumed to have been prepared by mixing white with blue and red.

In most of these pigments, small amounts of synthetic pigment components from the modern era were detected at many points. In addition, a detailed further examination of the cross-section of the pigment layer is required because of the overlap between the traditional pigments and the modern pigments that were used for repair. In addition, according to the pigment analysis results, the components Ca, Fe, As, and Cu were detected in nearly

all pigments. This indicates the presence of a filler or dead color paint for silk, which was used as the ground layer for many paintings.

The compositional analysis of the pigments in this study was limited to sampling, which allowed only non-destructive analysis and local analysis on exfoliated tiny samples that were recoverable. Additionally, the analysis results were compared to previously reported data. This preliminary study aims to secure the basic data necessary for preservation and restoration. The study's findings have been utilized as important data in selecting pigments to repair *White-Robed Water-Moon Avalokiteshvara* in Magoksa Temple, as well as for the restoration of damaged areas and long-term preservation.

Abbreviations

LBG: Blue-1; SB: Blue-2; BG: Green; OY: Yellow-1; Y: Yellow-2; R: Red; BL: Black; W: White; V: Violet; P: Pink.

Acknowledgements

Not applicable.

Authors' contributions

All authors contributed to the planning, design of this article, performed the data acquisition and data analysis, and HRY, JY and CHL wrote the manuscript and all authors revised it critically. All authors read and approved the final manuscript.

Funding

Not applicable.

Availability of data and materials

Not applicable.

Declarations

Competing interests

The authors declare that they have no competing interests.

Received: 17 September 2021 Accepted: 17 September 2021

Published online: 30 October 2021

References

1. Son Y, Kang DI, Lee HS, Lee HH. Comparative study on the pigments applied on the wall paintings of temple in 18~19C. *J Conserv Sci*. 2013;29(4):445–50 (in Korean with English abstract).
2. Lee CH, Yi JE, Han NR. Characterization and analysis of painted pigments for the clay statues in Donggwanwangmyo shrine, Seoul. *J Conserv Sci*. 2012;28(2):101–12 (in Korean with English abstract).
3. Yi JE, Han NR, Lee CH. Interpretation of making techniques and nondestructive diagnosis for the clay statues in Donggwanwangmyo shrine, Seoul. *J Conserv Sci*. 2013;29(1):35–45 (in Korean with English abstract).
4. Lee YJ, Kim JW, Han MS, Kang DI. Effect to the discoloration of lead based pigments by the factors of air environment. *J Conserv Sci*. 2018;34(2):69–76 (in Korean with English abstract).
5. Kim DW, Moon MJ, Lee DU, Kim IK, Kim MH. The study of discoloration of traditional paintings prepared by Azurite and Malachite pigments. *J Kor Soc Imag Sci Tech*. 2017;23(4):59–65 (in Korean with English abstract).
6. Mun SW, Kang YS, Kim JS, Hwang GH, Park JH, Lee SM, Jeong HY. Analysis on characteristics of pigments manufactured with various Neorok produced from Mt. Gwangjeongsan, Pohang. *J Conserv Sci*. 2020;36(6):533–40 (in Korean with English abstract).

7. Kim MJ, Lee JH, Doh JM, Ahn HS, Kim HD, Yang YM, Lee YH. Characterization of ancient Korean pigments by surface analytical techniques. *Surf Interface Anal.* 2016;48(7):409–14 **(in Korean with English abstract)**.
8. Park JS. Korean Buddhist paintings and their materials and technique. *Dongak Art History.* 2013;15:327–50 **(in Korean with English abstract)**.
9. Kim SK, Heo JS, Lee HH, Seo MS, Han MS. Composition analysis of painted pigments for the Jeoguibon (Patterns of the Queen's Ceremonial Robe) in Changdeok Palace. *J Conserv Sci.* 2013;29(4):379–88.
10. Kim JS, Lee CH. Interpretation of coloring technique and pigment analysis for King Sejo's Palanquin in Gongju Magoksa temple, Korea. *J Conserv Sci.* 2019;35(5):403–15 **(in Korean with English abstract)**.
11. Lee CH, Jo YH, Kim J. Damage evaluation and conservation treatment of the tenth century Korean rock-carved Buddha statues. *Environ Earth Sci.* 2011;64(1):1–14.
12. Jo YH, Lee CH, Chun YG. Material characteristics and deterioration evaluation for the 13th century Korean stone pagoda of Magoksa temple. *Environ Earth Sci.* 2012;66(3):915–22.
13. Gasanova S, Pagès-Camagna S, Andriotti M, Hermon S. Non-destructive in situ analysis of polychromy on ancient Cypriot sculptures. *Archaeol Anthropol Sci.* 2018;10(1):83–95.
14. Kogou S, Lucian A, Bellesia S, Burgio L, Bailey K, Brooks C, Liang H. A holistic multimodal approach to the non-invasive analysis of watercolour paintings. *Appl Phys A Mater Sci Process.* 2015;121(3):999–1014.
15. Li GH, Chen Y, Sun XJ, Duan PQ, Lei Y, Zhang LF. An automatic hyperspectral scanning system for the technical investigations of Chinese scroll paintings. *Microchem J.* 2020;155:104699.
16. Liu ZF, Zhang H, Zhou WH, Hao SC, Zhou Z, Qi XK, Shi JL. Pigment identification on an undated Chinese painting by non-destructive analysis. *Vib Spectrosc.* 2019;101:28–33.
17. Tortora M, Sfarra S, Chiarini M, Daniele V, Taglieri G, Cerichelli G. Non-destructive and micro-invasive testing techniques for characterizing materials, structures and restoration problems in mural paintings. *Appl Surf Sci.* 2016;387:971–85.
18. Wang J, Hao S, Zhou W, Qi X, Shi J. Research based on optical Non-destructive testing of pigment identification. *J Nanosci Nanotechnol.* 2016;16(4):3583–6.
19. Lei Z, Wu W, Shang G, Wu Y, Wang J. Study on colored pattern pigments of a royal Taoist temple beside the Forbidden City (Beijing, China). *Vib Spectrosc.* 2017;92:234–44.
20. Nöller R. Cinnabar reviewed: characterization of the red pigment and its reactions. *Stud Conserv.* 2015;60(2):79–87.
21. Lantes-Suárez Ó, Prieto B, Prieto-Martínez MP, Ferro-Vázquez C, Martínez-Cortizas A. The colour of ceramics from Bell Beaker contexts in NW Spain: relation to elemental composition and mineralogy. *J Archaeol Sci.* 2015;54:99–109.
22. McLellan MR, Lind LR, Kime RW. Hue angle determinations and statistical analysis for multiquadrant Hunter L, a, b data. *J Food Qual.* 1995;18(3):235–40.
23. Molari R, Appoloni CR. Pigment analysis in four paintings by Vincent van Gogh by portable X-ray fluorescence (pXRF). *Radiat Phys Chem.* 2021;181:109336.
24. Moretto LM, Orsega EF, Mazzocchin GA. Spectroscopic methods for the analysis of celadonite and glauconite in Roman green wall paintings. *J Cult Herit.* 2011;12(4):384–91.
25. Snickt GVD, Janssens K, Dik J, Nolf WD, Vanmeert F, Jaroszewicz J, Cotte M, Falkenberg G, Loeff LVD. Combined use of synchrotron radiation based micro-X-ray fluorescence, micro-X-ray diffraction, micro-X-ray absorption near-edge, and micro-Fourier transform infrared spectroscopies for revealing an alternative degradation pathway of the pigment cadmium yellow in a painting by Van Gogh. *Anal Chem.* 2012;84(23):10221–8.
26. He L, Wang N, Zhao X, Zhou T, Xia Y, Liang J, Rong B. Polychromic structures and pigments in Guangyuan Thousand-Buddha Grotto of the Tang Dynasty (China). *J Archaeol Sci.* 2012;39(6):1809–20.
27. De Viguierie L, Beck L, Salomon J, Pichon L, Walter P. Composition of Renaissance paint layers: simultaneous particle induced X-ray emission and backscattering spectrometry. *Anal Chem.* 2009;81(19):7960–6.
28. Smith GD, Clark RJH. Raman microscopy in archaeological science. *J Archaeol Sci.* 2004;31(8):1137–60.
29. Zięba-Palus J. Examination of the variation of chemical composition and structure of paint within a car body by FT-IR and Raman spectroscopies. *J Mol Struct.* 2020;1219:128558.
30. Lee JJ, Ahn JY, Yoo YM, Lee KM, Han MS. Diagnosis of coloration status and scientific analysis for pigments to used large Buddhist painting (Gwaebultaeng) in Tongdosa temple. *J Conserv Sci.* 2017;33(6):431–42 **(in Korean with English abstract)**.
31. Oh JS, Choi JE, Choi YH. Study on the copper-arsenic green pigments used on shamanic paintings in the 19–20th century. *J Conserv Sci.* 2015;31(3):193–214 **(in Korean with English abstract)**.
32. Yun EY, Chang YH. Analysis of pigment on portraits of Sim Hui-su in Joseon Period. *J Conserv Sci.* 2016;32(4):571–8 **(in Korean with English abstract)**.

Publisher's Note

Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Submit your manuscript to a SpringerOpen[®] journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

Submit your next manuscript at ► [springeropen.com](https://www.springeropen.com)